




INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G06K 19/06, G11B 5/70, 5/852	A1	(11) International Publication Number: WO 99/00766 (43) International Publication Date: 7 January 1999 (07.01.99)
(21) International Application Number: PCT/GB98/01829 (22) International Filing Date: 22 June 1998 (22.06.98) (30) Priority Data: 9713592.5 28 June 1997 (28.06.97) GB (71) Applicant (for all designated States except US): THORN SECURE SCIENCE LIMITED [GB/GB]; Rutland House, Hargreaves Road, Groundwell Industrial Estate, Swindon, Wiltshire SN2 5AZ (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): BUSSELL, Simon, Jason [GB/GB]; 21 High Street, Purton, Swindon, Wiltshire SN5 9AE (GB). (74) Agent: LEAMAN, Keith; QED I.P. Services Limited, Dawley Road, Hayes, Middlesex UB3 1HH (GB).		(81) Designated States: AU, CN, JP, KR, US, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the</i> <i>claims and to be republished in the event of the receipt of</i> <i>amendments.</i>
(54) Title: A MAGNETIC RECORDING MEDIUM (57) Abstract <p>A magnetic recording medium comprises a layer of material including permanently aligned acicular magnetic particles having a first coercivity, and magnetic particles having a further coercivity higher than the first. The ratio of the volume per unit area of particles having said first coercivity to the volume per unit area of particles having said further coercivity is preferably between 3.4:6.6 and 5.5:4.5, and the particles having the further coercivity preferably comprise either barium ferrite or strontium ferrite platelets. The layer may be carried by a flexible substrate thereby forming a tape which can simultaneously record data permanently by means of the acicular particles and erasably by means of the particles having the further coercivity. The layer is manufactured using a slurry containing a mixture of the two types of particle, and a two stage alignment process.</p>		



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

A MAGNETIC RECORDING MEDIUM

This invention relates to a magnetic recording medium comprising a layer of material including permanently aligned acicular magnetic particles having a given coercivity. This invention also relates to methods of making such a magnetic recording medium.

A known magnetic recording medium of this type is described in GB-B-1 331 604, in which acicular particles of γ -Fe₂O₃ (having a coercivity of perhaps 27 kA/m) are fixedly aligned in predetermined directions in selected spaced regions of the layer, the regions in between either being randomly aligned or being aligned in a different direction. This type of magnetic recording medium is manufactured in the form of a tape by Thorn Secure Science International Limited under the Trade Mark "WATERMARK" tape.

"WATERMARK" tape provides high security because the permanently recorded data is difficult to counterfeit, and gives the option to write ordinary data on the magnetic stripe compatible with ISO standard low coercivity (LoCo) bank cards.

In recent years there has been a growth in the use of high coercivity (HiCo) magnetic records, for example as tape on credit or bank cards or other documents of value. Such material typically has a coercivity of above about 1200 Oe (i.e. 100 kA/m) and is described more fully in the standards document ISO 7811/6. Such HiCo magnetic records offer better resistance to erasure than LoCo materials, but do not offer the high security possible with "WATERMARK" tape.

A combination of the two technologies would offer both security and resistance to accidental erasure, but attempts to combine the two materials have up until now been unsuccessful. Such attempts have included tracks manufactured side by side or laminated one on top of the other.

According to one aspect of the present invention there is provided a magnetic recording medium comprising a layer of material including permanently aligned acicular magnetic particles having a first coercivity, characterised in that the layer also includes magnetic particles having a further coercivity higher than the first.

This magnetic recording medium combines LoCo and HiCo technologies without the problems associated with aligning different materials side by side, or the difficulty of reading one layer through the other. The medium can be used simultaneously to record data permanently by means of the acicular particles

and erasably by means of the particles having the further coercivity. The medium enables the permanent data to be read in the presence of soft encoded HiCo data using existing equipment.

5 The present invention also enables hand held reader units to be used without problems caused by the active head of the "Watermark" data reader erasing soft encoded data on neighbouring tracks of tape having only LoCo particles. This is a problem because of the inability precisely to align hand held readers with the correct tape track reliably in use.

10 Preferably, the volume percent of particles having said first coercivity is less than the volume percent of particles having said further coercivity. This enables the medium to conform to standards document ISO 7811/6 by reducing the distortion produced by crosstalk between the two types of record.

15 According to a second aspect of the invention there is provided a method of making a magnetic recording medium, including:

- a) preparing a slurry including acicular magnetic particles having a first coercivity and non-acicular magnetic particles having a further coercivity higher than the first coercivity,
- b) coating the slurry onto a flexible substrate to form a layer,
- 20 c) aligning the acicular magnetic particles in said layer , and
- d) solidifying said layer.

According to a third aspect of the invention there is provided a method of making a magnetic recording medium, including:

- 25 a) preparing a slurry including acicular magnetic particles having a first coercivity,
- b) adding non-acicular magnetic particles having a further coercivity higher than the first coercivity to the slurry,
- c) coating the slurry onto a flexible substrate to form a layer,
- 30 d) aligning the acicular magnetic particles in said layer , and
- e) solidifying said layer.

The invention relates particularly, though not exclusively, to magnetic records for credit or bank cards or other documents of value.

35

Embodiments of the invention will now be described, by way of example only, with reference to the accompanying diagrammatic drawings, in which :-

- Figure 1 shows a flow diagram of a method according to the invention,
Figure 2 shows a flow diagram of a second method according to the invention,
Figure 3 shows a plan view of a layer of a magnetic recording medium having HiCo particles,
5 Figure 4 shows an oblique view of the medium of Figure 3,
Figure 5 shows a plan view of a layer of a magnetic recording medium according to the invention,
Figure 6 shows the layer of Figure 5 having a permanently aligned structure,
Figure 7 shows a theoretical hysteresis curve for a magnetic recording medium
10 according to the invention, and
Figure 8 shows a measured hysteresis curve for a magnetic recording medium according to the present invention.

15 A magnetic recording medium having a mixture of hexagonal platelets and acicular particles is disclosed in US 4,657,813. However, in this prior art document the alignment is performed after the slurry has been solidified, so the acicular particles do not have a permanently oriented structure.

20 Figure 1 shows a flow diagram of a method of making a magnetic recording medium. The numbered blocks in the diagram have the following significances.

Block 1 of Figure 1 denotes preparing a slurry including acicular magnetic particles having a first coercivity and non-acicular magnetic particles having a further coercivity larger than the first coercivity. A number of
25 examples of how to produce a slurry in accordance with the present invention are described below.

EXAMPLE 1

30 In the present example the slurry is prepared in the following way. Powdered γ -Fe₂O₃ in the form of agglomerates of acicular individual grains is dispersed into a liquid mixture of a binder and a solvent using a stirring apparatus which provides significant shear forces. This mixture is then fed into a bead mill and milled to separate the individual grains to form a slurry. In this
35 first example the exact slurry composition used has a solids content of 56% and the solvent used is a mixture of toluene and methyl ethyl ketone. The composition of the solids is as follows (in weight %):- polyester resin 7.1%,

polyurethane resin 6.2%, phosphate surfactant 0.6%, de-oiled lecithin 0.6%, carbon black 1.3%, γ -Fe₂O₃ 31.1%, barium ferrite 50.2%, lubricant 1.5% and melamine curing agent 1.3%.

Care needs to be taken during preparation of the slurry as the LoCo particles (γ -Fe₂O₃) and the HiCo particles (barium ferrite) have different properties. The barium ferrite particles obtained in powdered form are smaller than the LoCo particles and have a lower oil adsorption, thus making them far easier to disperse than the LoCo particles. If both magnetic pigments were loaded into the bead mill at the same time the barium ferrite would be overmilled and the dispersion would become unstable. In particular, the HiCo particles will tend to come out of suspension, leading to changes in the viscosity of the slurry and hence the quality of the coating and quality of the subsequent watermarking.

Three possible methods of overcoming this problem are

- a) to make two separate dispersions and mix them afterwards,
- b) add the HiCo particles very late in the milling process, or
- c) to stir the HiCo particles directly into the slurry.

The latter technique is especially advantageous if strontium ferrite is the HiCo material. Other HiCo materials such as Platinum - Cobalt or Silmanol may be used alternatively or in addition.

The preferred ranges employed for the above listed ingredients in the present embodiment are as follows:-

polyester resin 4 - 20%,
polyurethane resin 4 - 20%,
phosphate surfactant 0 - 2%,
de-oiled lecithin 0 - 2%,
carbon 0.5 - 6%,
alumina 0 - 5%
silica 0 - 5%
 γ -Fe₂O₃ 20 - 80%,
barium ferrite 20 - 80%,
isocyanate or melamine curing agent 0 - 5%.
lubricant (e.g. silicone or PTFE oil) 0 - 3%

Suitable solvents include one or more of the group including toluene, methyl ethyl ketone and methyl iso-butyl ketone.

The volume ratio of LoCo particles to HiCo particles is preferably
5 between 3.4:6.6 and 5.5:4.5. Pigment volume content is typically between 50 and 55%, and the preferred solid content is between 40 and 60%.

It should be noted that in this example the pigment loading is far higher than that normally used for standard tape. The pigment loading levels are chosen such that the LoCo watermark of the subsequent tape is readable, and the
10 HiCo record can pass the "window" test of standards document ISO /IEC 7811 - 6. The standard does not specify a minimum coercivity for the tape, but is difficult to pass unless the finished tape has a coercivity of above about 1200 Oe (i.e. 100 kA/m). Tape made using the slurry described above typically has a coercivity approximately equal to or greater than 1500 Oe (125 kA/m).

15

EXAMPLE 2

As a further example of a way of producing a slurry as described above, the following formulation is used to make up two separate slurries (denoted part
20 A and part B) which are subsequently mixed in equal portions by weight to produce the final mixture.

PART A

strontium ferrite 92.6 wt%
25 functionalised vinyl resin 7.4 wt%
prepared as a slurry having a solid content of 40% in a solvent as above.

PART B

modified PVC resin 5.7 wt%
30 polyurethane resin 14.4 wt%
phosphate surfactant 1.4 wt%
de-oiled lecithin 1.4 wt%
carbon black 3.0 wt%
 γ -Fe₂O₃ 71.8 wt%
35 lubricant (e.g. silicone or PTFE oil) 2.3 wt%
prepared as a slurry having a solid content of 40% in a solvent as above.

EXAMPLE 3

Formulations in the following ranges may also be used to prepare a slurry for use in the present invention:-

functionalised vinyl co-polymer 0.6 - 20 wt%

5 γ ferric oxide 20 - 80 wt%

carbon 0.5 - 6%

alumina 0 - 5%

silica 0 - 5%

polyester resin 5 - 20%

10 polyurethane resin 5 - 20%

strontium or barium ferrite 20 - 80%

isocyanate or other curing agent 0 - 5%

lubricant (e.g. silicone or PTFE oil) 0 - 3%.

15 The volume ratio of LoCo particles to HiCo particles is preferably between 34:66 and 55:45. Pigment volume content is typically between 50 and 55%, and the preferred solid content is between 40 and 60%. Suitable solvents include one or more of the group including toluene, methyl ethyl ketone and methyl iso-butyl ketone.

20 Once the slurry has been prepared according to one of the above recipes it is coated onto a flexible substrate to form a layer. This step is denoted by block 2 in Figure 1. The flexible substrate may comprise, for example, a polyester film as used in magnetic tape manufacture, a sheet of paper or card, or a sheet of plastics material. In the present example polyester film is employed as a
25 substrate, and the rest of the fabrication process is similar to the manufacture of "WATERMARK" tape as described in, for example, GB - B - 1 331 604. However, in the present example the thickness of the layer is preferably controlled to have a constant value in the range between 15 and 30 micrometers. This enables the finished tape or card to pass the criteria established in the standards document
30 ISO/IEC 7811 - 6.

Once the layer has been formed on the substrate, the acicular LoCo particles (γ ferric oxide particles in the present example) are aligned in the usual way (as described in GB - B - 1 331 604) to form selected spaced regions in which the LoCo particles are aligned along a predetermined direction, and the LoCo
35 particles in the remainder of the layer are either not so aligned or are aligned along a substantially different direction. This is denoted by block 3 in Figure 1.

The fluid layer is then solidified in the usual way (as described in GB -B - 1 331 604) so that the alignment of all the magnetic particles becomes fixed. This is denoted by block 4 in Figure 1.

Figure 2 also shows a flow diagram of a method of making a magnetic recording medium in accordance with the present invention. Blocks 2 - 4 have the same significance as in Figure 1, but additional blocks 5 and 6 have replaced block 1. In this diagram block 5 denotes preparing a slurry including acicular magnetic particles having a first coercivity, whilst block 6 denotes adding non-acicular magnetic particles having a further coercivity higher than the first coercivity to the slurry.

Figure 4 shows a cross section of what the layer looks like in cross-section after the initial alignment. The barium ferrite particles (10) are normally in the form of hexagonal platelets, having an easy axis of orientation (15) normal to the plane of the platelet. The acicular particles are not shown in this Figure to improve clarity. They are shown however in Figures 5 and 6. The barium ferrite particles in the layer form columns (14) as shown in plan view in Figure 3, the columns having being oriented parallel to one another, the axes of the generally cylindrical columns corresponding to an easy axis of orientation (15) normal to the axis of the orienting magnetic field (16). Each column resembles a stack of coins arranged with the surface of each coin substantially normal to the surface of the substrate.

The ferric oxide particles (11) are generally elongate or acicular, having magnetic properties which have a single axis of symmetry along the long axis of the particle. The thickness of the layer in this example is 22 micrometers, and in this example it is carried by a flexible polyester substrate (12). Figure 5 shows a plan view of the layer after its initial orientation step which aligns all the particles in the way shown with the axes of the acicular particles substantially orthogonal to the axes of the columns of platelets. This initial orientation is performed using a magnetic field of the order of 100 - 350 milliTesla to ensure both the HiCo and LoCo particles are aligned.

Figure 6 shows the same layer having been given a further alignment to form regions 20 and 21 having different magnetic properties from one another, thereby forming a permanently aligned structure after solidification which can be used to store data which cannot subsequently be erased. In this further alignment (in which the alignment of the acicular magnetic particles only is changed in spaced regions 21) a magnetic field of only 8 - 20 milliTesla is

employed so that the HiCo particles are not realigned to the same extent as the LoCo particles.

Figure 8 shows a typical hysteresis curve for a magnetic recording medium made according to example 1 above. Typical values of coercivity are
5 between 1200 and 4000 Oe (125 to 340 kA/m), preferably between 1500 and 2500 Oe, the saturation magnetisation is typically 0.5 to 0.9 emu, and the remanence is of the order of 0.3 to 0.7 emu. A theoretical prediction of what the hysteresis curve should look like is shown in Figure 7.

The tape made according to the foregoing instructions may optionally
10 have a lacquer overcoat applied to provide protection to the surface during use.

An unsupported layer may be produced by peeling away the flexible substrate. This process will be easier if a release layer has been provided between the layer and the substrate during manufacture.

CLAIMS

1. A magnetic recording medium comprising a layer of material including permanently aligned acicular magnetic particles having a first coercivity, the
5 layer including magnetic particles having a further coercivity higher than the first characterised in that data is recorded permanently by means of the acicular particles and erasably by means of the particles having the further coercivity.
2. A magnetic recording medium as claimed in claim 1 in which the magnetic
10 particles having said further coercivity are platelets.
3. A magnetic recording medium as claimed in any preceding claim, in which the ratio of the volume percent of particles having said first coercivity to the volume percent of particles having said further coercivity is between 34:66 and 55:45.
- 15 4. A magnetic recording medium as claimed in any preceding claim in which the particles having said further coercivity comprise one or more of the group of materials including barium ferrite, strontium ferrite, Platinum - Cobalt and Silmanol.
5. A magnetic recording medium as claimed in any preceding claim in which the
20 layer is carried by a flexible substrate.
6. A document of value carrying a magnetic recording medium as claimed in any preceding claim.
7. A method of making a magnetic recording medium, including:
 - 25 a) preparing a slurry including acicular magnetic particles having a first coercivity and non-acicular magnetic particles having a further coercivity higher than the first coercivity,
 - b) coating the slurry onto a flexible substrate to form a layer,
 - c) aligning the acicular magnetic particles in spaced regions of said layer, and
 - 30 d) solidifying said layer.
8. A method of making a magnetic recording medium, including:
 - a) preparing a slurry including acicular magnetic particles having a first coercivity,
 - 35 b) adding non-acicular magnetic particles having a further coercivity higher than the first coercivity to the slurry,
 - c) coating the slurry onto a flexible substrate to form a layer,

d) aligning the acicular magnetic particles in spaced regions of said layer,
and

e) solidifying said layer.

- 5 9. A method of making a magnetic recording medium as claimed in claim 7 or claim 8 in which the volume percent of particles having said first coercivity and the volume percent of particles having said further coercivity in the slurry are in a ratio between 34:66 and 55:45.

Fig.1.




Fig.2.




Fig.3.




Fig.4.




Fig.5.





Fig.6.



SUBSTITUTE SHEET (RULE 26)

Fig.7.





Fig.8.



INTERNATIONAL SEARCH REPORT

In International Application No

P 98/01829

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 G06K19/06 G11B5/70 G11B5/852

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 G06K G11B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US 4 281 043 A (DEFFEYES ROBERT J) 28 July 1981 see column 3, line 47 - line 54 see column 6, line 47 - line 59 see column 9, line 32 - line 37; figure 2 see column 13, line 3 - line 7 ----	1-9
A	US 3 986 205 A (FAYLING RICHARD E) 12 October 1976 see column 1, line 58 - column 2, line 19 see column 5, line 34 - line 43 see claims 1-5 ----	1-9
A	US 4 197 989 A (PEARCE RALPH R) 15 April 1980 see column 4, line 34 - column 5, line 9 see claim 1; figure 3 -----	1-9

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

26 October 1998

Date of mailing of the international search report

04/11/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Klocke, S

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

P 98/01829

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4281043 A	28-07-1981	US 4237189 A	02-12-1980
		BE 823013 A	01-04-1975
		CA 1079514 A	17-06-1980
		DE 2451796 A	07-05-1975
		FR 2257957 A	08-08-1975
		GB 1493944 A	30-11-1977
		JP 1156134 C	15-07-1983
		JP 50085306 A	09-07-1975
		JP 57033601 B	17-07-1982
US 3986205 A	12-10-1976	NONE	
US 4197989 A	15-04-1980	DE 2545959 A	29-04-1976
		US 4104513 A	01-08-1978